

PAPER • OPEN ACCESS

## Effect of coir fibre and clayey soil on the strength of unglazed roofing tiles

To cite this article: O D Atoyebi *et al* 2020 *IOP Conf. Ser.: Earth Environ. Sci.* **445** 012030

View the [article online](#) for updates and enhancements.

# Effect of coir fibre and clayey soil on the strength of unglazed roofing tiles

O D Atoyebi<sup>1</sup>, B O Orogbade<sup>1</sup>, T M A Olayanju<sup>2</sup>, A A Okunola<sup>2</sup> and A J Oyetayo<sup>1</sup>

<sup>1</sup>Department of Civil Engineering, Landmark University, Omu-Aran, Kwara State.

<sup>2</sup>Department of Agric & Biosystems Engineering, Landmark University, Omu-Aran, Kwara State

Corresponding Author; atoyebi.olumoyewa@lmu.edu.ng

**Abstract.** Agricultural waste based roofing materials can be useful in the construction of farm structures and green buildings. This study evaluated the transverse breaking strength, flexural strength and Water Absorption properties of concrete roofing tile replacing the conventionally used sisal fiber which provides transverse strength with coir fiber and plaster sand with clay soil. Five roofing tile samples of different mix design were produced. The result attained for the flexural test and transverse breaking strength for all roofing tile samples at 28 days test showed that roofing tile replace with 100% coir fiber can also be used commercially although it is not as strong as the roofing tile with 100% coir fiber. The result attained for water absorption was within the acceptable value according to ASTM C1492.

## 1. Introduction

Civilizations in China (Neolithic) and the Middle East has revealed the positive properties of clay tiles as a roofing material which are its good fire resistance and effectivity in water repellent from buildings [1]. The need to develop a cheaper and lightweight clay tile has resulted in the use of clay and bamboo fiber for roof covering. Clays (and clay minerals) are products of in situ alterations or deposited as sediment during erosional cycle or developed in situ as antigenic clay deposit [2]. There are many different clay minerals available in commercial quantity that can be used for industrial applications in Nigeria. Interests are on the increase in the construction sector on the use of clay products as against the neglect it has experienced in the last decades [3]. The quality variation in clay production is mainly due to fluctuation in raw material mineralogical composition, the degree of firing and the difference in the manufacturing method. Mineralogical content of clay soil is one of the most important factors which determine the quality of burnt clay bricks. Silica and alumina makes the main composition of clay with additions of metallic oxides and impurities [4–7]. Clay is the basic materials in the production of roof tiles. The unique plastic characteristics of clay soil are a result of the enormous amount of surface area inherent in the particle size and shape, these characteristics makes it suitable in the production of roof tiles. When mixed with water, its plasticity allows it to be easily shaped into desired forms with the use of moulds and the formed shapes are easily maintained after been demoulded due to its good tensile strength. Clay particles are highly fused at high temperatures [8].



Industrialization has been attracted by biodegradability and environmental protection benefits in natural plant fibres, using its composites to develop variety of products [9–12]. Coconut being a product from the palm tree has been proved to be the most versatile fruit used with every part of the tree found useful across different countries in numerous ways [13–18]. Coconut fiber materials have attracted broad attention as reinforcement polymer composites due to their environmental sustainability, mechanical properties, and recyclability, and they can be compared with glass fibers. Among the natural fibers, Coconut fiber can be suitably used as reinforcing materials due to its higher fracture toughness, easy availability at low cost and rapid renewability [19,20]. Numerous research works have been done on the different parts of Coconut, its parts have been utilized in construction activities, for example, coconut shell [19,21–23], coconut husk [24,25], coconut ash [26] etc.

## 2. Methodology

The materials used for this research are Plaster sand, Clay soil, Sharp sand, Coir fiber, Sisal fiber, Water (portable), Cement and the Bolyn Roman Tile Vibrating Table. The cement was used as a binder in the production of roofing tile while the fiber is used to increase the flexural strength, sharp sand was used to provide compressive strength for the roofing tile, while plaster sand makes the roofing tile surface smooth. The Bolyn Roman Tile Vibrating table is used to remove void from roofing tile. The coir fiber and sisal fiber were cut to  $25\pm 3$  mm length, batching method used was by volume using ratio 1:1.5:1.5 which is cement, sharp sand and plaster sand respectively. Table 1 shows the percentage mix for each material in the different roofing tile compositions. The materials were mixed thoroughly to form a homogenous mix before the addition of water. The mixture was placed in Bolyn Roman Tile Vibrating Table and vibrated manually. Thereafter, the vibrated mortar was placed in formwork, smoothed and air-dried for about 24 hours before curing.

**Table 1.** Unglazed Roofing Tile Experimental Design.

	Fiber Sisal	Coir Fibre	Plaster Sand	Clay Soil
S <sub>100</sub> C <sub>0</sub> P <sub>100</sub> CL <sub>0</sub>	100%	-	100%	-
S <sub>50</sub> C <sub>50</sub> P <sub>90</sub> CL <sub>10</sub>	50%	50%	90%	10%
S <sub>0</sub> C <sub>100</sub> P <sub>90</sub> CL <sub>10</sub>	-	100%	90%	10%
S <sub>50</sub> C <sub>50</sub> P <sub>100</sub> CL <sub>0</sub>	50%	50%	100%	-
S <sub>0</sub> C <sub>100</sub> P <sub>100</sub> CL <sub>0</sub>	-	100%	100%	-

## 3. Result and discussions

The Water absorption and average mass of the tiles produced are given in table 2. The composite with 50% coir fibre, 10% clay has the highest water absorption value (17.765%), ASTM C1492 states the allowable water absorption ranges from 10.5% to 18%, all the roofing tile samples are within the acceptable range [27]. The transverse breaking strength (TBS) and flexural strength are presented in table 3. ASTM C1492 states the acceptable TBS to be 700N minimum, in which all samples pass acceptability except for 100% coir fibre and 100% plaster sand [27].

**Table 2.** Mean Water Absorption and Mass of Unglazed Tiles.

Sample	Mean Water Absorption (%)	Mass (Kg)
S <sub>100</sub> C <sub>0</sub> P <sub>100</sub> CL <sub>0</sub>	15.245	4.92

$S_{50}C_{50}P_{90}CL_{10}$	17.765	5.24
$S_0C_{100}P_{90}CL_{10}$	15.644	5.32
$S_{50}C_{50}P_{100}CL_0$	16.764	5.1
$S_0C_{100}P_{100}CL_0$	16.021	4.82

**Table 3.** Mean Transverse Breaking and Flexural Strength Values of Unglazed Tiles.

Sample	Transverse Breaking Strength (N/mm <sup>2</sup> )			Flexural Strength (N/mm <sup>2</sup> )		
	7 Days	14 Days	28 Days	7 Days	14 Days	28 Days
$S_{100}C_0P_{100}CL_0$	480.637	673.139	806.729	3.493	4.892	5.863
$S_{50}C_{50}P_{90}CL_{10}$	469.491	624.979	781.293	3.412	4.892	5.678
$S_0C_{100}P_{90}CL_{10}$	455.731	597.597	720.198	3.312	4.343	5.234
$S_{50}C_{50}P_{100}CL_0$	461.235	611.357	705.338	3.352	4.443	5.326
$S_0C_{100}P_{100}CL_0$	452.704	587.139	677.68	3.29	4.267	4.925

Roofing tile composite  $S_{100}C_0P_{100}CL_0$  performed better in strength compared to all other samples. This implies that roofing tiles with sisal fiber performs better in strength than coir fiber. Also, the transverse breaking strength and flexural strength of samples  $S_{50}C_{50}P_{90}CL_{10}$  and  $S_0C_{100}P_{90}CL_{10}$  in which plaster sand is replaced with 10% clay soil performed better than samples with 100% plaster sand. This shows that clay soil gives an added advantage in strength to the roofing tiles.

$S_{50}C_{50}P_{90}CL_{10}$  having 10% clay has the highest water absorption while samples with clay have averagely lower water absorption values. Also all the roofing tile samples are within the acceptable water absorption value according ASTM C1492. There is increase in mass with increase in clay in roofing tile  $S_{50}C_{50}P_{90}CL_{10}$  and  $S_0C_{100}P_{90}CL_{10}$ . This implies increase in clay soil causes increase in soil mass.

#### 4. Conclusion

The roofing tiles with sisal fiber performs better in strength than coir fiber. The roofing tiles with 10% clay soil has better transverse breaking strength and flexural strength. The water absorption value and the mass increases with increase in the clay sample. It is recommended that sisal fibre should be encouraged, the use of coir fibre should be limited to small percentage and with high sisal fibre volume. Clay soil should be discouraged for light weight roofing tiles and low water absorption properties.

#### Acknowledgements

The authors wish to acknowledge the support offered by Landmark University in the actualization of this research work for publication

## References

- [1] Adegoke C W and Abiodun F 2015 Development of an improved concrete roman tile alternative roofing system using waste raw materials (paper & saw dust) as additives *Int J Sci and Technology Res* **4** 5 1-7
- [2] Olubayode S A, Awokola O S, Dare E O and Olateju O T 2016 Suitability of selected Nigeria clay deposit for Production of Clay Based Ceramic Water Filters *Am Chem Sci J* **12** 3 1–7. doi:10.9734/ACSJ/2016/23175
- [3] Liblika A J 2016 Performance of Constructions with Clay Plaster and Timber at Elevated Temperatures. *Tallinn Helsinki Conf Build Green Renov. Deep* 717–28.
- [4] Chemani B and Chemani H 2012 Effect of Adding Sawdust on Mechanical- Physical Properties of Ceramic Bricks to Obtain Lightweight Building Material *Int J Mech Aerospace, Ind Mechatron Manuf Eng* **6**:2521–5.
- [5] De Silva G H M J S and Surangi M L C 2017 Effect of waste rice husk ash on structural, thermal and run-off properties of clay roof tiles *Constr Build Mater* **154** 251–7. doi:10.1016/j.conbuildmat.2017.07.169.
- [6] Adebisi N O, Adebisi G O, Oluwafemi O S and Songca S P 2013 Important Properties of Clay Content of Lateritic Soils for Engineering Project *J Geogr Geol* **5** 99–115 doi:10.5539/jgg.v5n2p99.
- [7] Ibrahim N M, Salehuddin S, Amat R C, Liza N, Nuraiti T and Izhar T 2013 Performance of Lightweight Foamed Concrete with Waste Clay Brick as Coarse Aggregate *APCBEE Procedia* **5** 497–501. doi:10.1016/j.apcbee.2013.05.084.
- [8] Odeyemi S O, Akinpelu M A, Atoyebi O D and Yahaya R T 2017 Determination of Load Carrying Capacity of Clay Bricks Reinforced With Straw *Int J Sustain Constr Eng Technol* **8** 2 57–65
- [9] Atoyebi O D, Odeyemi S O, Azeez L O and Modupe A E 2019 Physical and Mechanical Properties Evaluation of Corncob and Sawdust Cement Bonded Ceiling Boards *Int J Eng Res Africa* **42** 65–75 doi:10.4028/www.scientific.net/JERA.42.65.
- [10] Atoyebi O D, Osueke C O, Badiru S, Gana A J, Ikpotokin I and Modupe A E 2019 Evaluation of Particle Board from Sugarcane Bagasse and Corn Cob *Int J Mech Eng Technol* **10** 1193–200
- [11] Atoyebi O D, Odeyemi S O and Orama J A 2018 Experimental data on the splitting tensile strength of bamboo reinforced lateritic concrete using different culm sizes *Data Br* **20** 1960–4. doi:10.1016/j.dib.2018.09.064.
- [12] Atoyebi O D, Awolusi T F and Davies I E E 2018 Artificial neural network evaluation of cement-bonded particle board produced from red iron wood ( *Lophira alata* ) sawdust and palm kernel shell residues *Case Stud Constr Mater* e00185. doi:10.1016/j.cscm.2018.e00185.
- [13] Tolêdo Filho R D, Scrivener K, England G L and Ghavami K 2000 Durability of alkali sensitive sisal and coconut fibres in cement based composites *Cement Concrete Comp* **6** 22 127–14. Doi:10.1016/S0958-9465(99)00039-6
- [14] Tolêdo R D, Ghavami K, England G L and Scrivener K 2003 Development of vegetable fibre-mortar composites of improved durability *Cem Concr Compos* **25** 185–96. doi:10.1016/S0958-9465(02)00018-5.
- [15] Ali M and Chouw N 2013 Experimental investigations on coconut-fibre rope tensile strength and pullout from coconut fibre reinforced concrete *Constr Build Mater* **41** 681–90. doi:10.1016/j.conbuildmat.2012.12.052.
- [16] Wang W and Chouw N 2017 The behaviour of coconut fibre reinforced concrete ( CFRC ) under

- impact loading *Constr Build Mater* **134** 452–61. doi:10.1016/j.conbuildmat.2016.12.092.
- [17] Chougale J and Pimple D 2014 Effects of coconut fibers on the properties of concrete *Int J Res Eng Technol* **3** 5–11
- [18] Adediran A A, Olawale O, Ojediran J, Aladegboye S, Atoyebi O D, Akinlabi E T 2019 Properties of agro-based hybrid particleboards *Procedia Manuf* **35** 442–6. doi:10.1016/j.promfg.2019.05.064.
- [19] Atoyebi O D, Osuolale O M, Ibitogbe E M 2019 Strength Evaluation of Cocos nucifera Fibre Reinforced Concrete. *J Eng Appl Sci* **14** 8061–6.
- [20] Savastano H, Santos S F and Agopyan V 2009 Sustainability of vegetable fibres in construction. *Sustain Constr Mater* 55–81 doi:10.1533/9781845695842.55.
- [21] Rocha R, Henrique C and Del S 2016 Utilization of the coconut shell of babaçu ( *Orbignya sp.* ) to produce cement - bonded particleboard **85** 1–2
- [22] Din MA BIN and Abdullah MS BIN 2014 Coconut shell as aggregate in concrete roof tiles Unpublished Diploma Thesis Universiti Teknikal Malaysia Melaka (UTeM), 2014.
- [23] Santoso D, Widigdo W K and Juniwati A 2015 Application of coconut fibres as outer eco-insulation to control solar heat radiation on horizontal concrete slab rooftop *Procedia Eng* **125** 765–72 doi:10.1016/j.proeng.2015.11.129.
- [24] Dam J E G Van, Oever M J A Van Den and Keijzers E R P 2004 Production process for high density high performance binderless boards from whole coconut husk *Industrial Crops and Products* **20** 1 97–101. doi:10.1016/j.indcrop.2003.12.017.
- [25] Ali M 2011 Coconut fibre: A versatile material and its applications in engineering *J Civ Eng Constr Technol* **2** 189–97. doi:10.1.1.823.5053.
- [26] Anifowoshe F and Nwaiwu N 2016 The Use of Coconut Fibre Ash as a Partial Replacement for Cement *Br J Appl Sci Technol* **17** 1–11. doi:10.9734/BJAST/2016/25926.
- [27] ASTM C1492 - 03 2016 Standard Specification for Concrete Roof Tile. West Conshohocken, PA: doi:10.1520/C1492-03R16.